

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Presently Amended) A composite material comprising a boehmite substrate coated with a precipitated silica, the composite having an Einlehner abrasion value of about 15 mg lost/100,000 revolutions to about 30 mg lost/100,000 revolutions, and a BET specific surface area of from 1 m²/g to 50 m²/g, such that the composite material has a %silica coating parameter value of 5% to 50%, based on the ratio of the weight of the precipitated silica to the total weight of the boehmite and precipitated silica.
2. (Original) The composite material according to claim 1, wherein the composite material has a median particle size of about 1μm to about 20μm.
3. (Original) The composite material according to claim 1, wherein the composite material has a median particle size of 1μm to 10μm.
4. (Cancelled)
5. (Original) The composite material according to claim 1, wherein the boehmite substrate has a median diameter of 1 μm to 20 μm.
6. (Original) The composite material according to claim 1, wherein the boehmite substrate has a median diameter of 1μm to 5μm.

7. (Original) The composite material according to claim 1, wherein the boehmite substrate has an Einlehner abrasion value of about 10 mg lost/100,000 revolutions to about 65 mg lost/100,000 revolutions.

8. (Original) The composite material according to claim 1, wherein the composite has a BET surface area of $1 \text{ m}^2/\text{g}$ to $10 \text{ m}^2/\text{g}$.

9. (Presently Amended) The composite material according to claim 1, wherein the %silica coating value is between 15% to 40%, based on the ratio of the weight of the precipitated silica to the total weight of the boehmite and silica.

10. (Original) The composite material according to claim 1, wherein the composite material has a %CPC compatibility value of greater than about 40%.

11. (Original) The composite material according to claim 1, wherein the composite material has a %CPC compatibility value of greater than about 55%.

12. (Original) The composite material according to claim 1, wherein the composite material has a %CPC compatibility value of greater than about 75%.

13. (Original) The composite material according to claim 1, wherein the composite material has a fluoride compatibility value of greater than about 40%.

14. (Original) The composite material according to claim 1, wherein the composite material has a fluoride compatibility value of greater than about 80%.

15. (Original) The composite material according to claim 1, wherein the composite material has a CPC compatibility value of greater than about 40% and a fluoride value compatibility of greater than about 40%.

16. (Original) The composite material according to claim 1, wherein the composite material has a CPC compatibility value of greater than about 70% and a fluoride

compatibility value of greater than about 80%.

17. (Presently Amended) A dentifrice containing a composite material comprising a boehmite substrate coated with a precipitated silica, the composite having a BET specific surface area of from $1 \text{ m}^2/\text{g}$ to $50 \text{ m}^2/\text{g}$, such that the composite material has a %silica coating parameter value of 5% to 50%, based on the ratio of the weight of the precipitated silica to the total weight of the boehmite and precipitated silica, and wherein the dentifrice PCR/RDA ratio is greater than 1.2.

18. (Previously Amended) The dentifrice according to claim 17, comprising about 10% to about 35% by weight of the composite particles based on the weight of the dentifrice.

19. (Cancelled)

20. (Original) The dentifrice according to claim 17, wherein the dentifrice PCR/RDA ratio is about 1.2 to about 1.5.

21. (Original) The dentifrice according to claim 17, wherein the dentifrice RDA value is greater than 60.

22. (Original) The dentifrice according to claim 17, further comprising one or more ingredients selected from the group consisting of abrasives, other thickeners, humectants, antibacterial agents, fluorides, flavors, sweeteners, and surfactants.

23. (Cancelled)

24. (Cancelled)

25. (Presently Amended) A method of forming a composite material that includes forming boehmite particles by adding aluminum trihydrate to an aqueous solution and then heating the aluminum trihydrate-containing aqueous solution, under a pressure of about 190 psi to 250 psi to form the boehmite particles, while simultaneously adding an acid to the aqueous solution containing alkali metal silicate, thereby depositing silica, which has a BET specific surface area of from $1 \text{ m}^2/\text{g}$ to $50 \text{ m}^2/\text{g}$, onto the boehmite particles to form a silica-treated boehmite composite material; the composite material having a %silica coating parameter value of 5% to 50%, based on the ratio of the weight of the precipitated silica to the total weight of the boehmite and precipitated silica.